

ELEMENTIS

**OBJECTIVE** 





- PS Matt 112 (waterbased)
- PS Matt 601 (solventbased)

to produce a matting paste with a minimum concentration of 20% for solution GmbH, Germany





















PS Matt 112 (waterbased)

ELEMENTIS

RESULTS % = concentration PS Matt 112

Additive 3


No Additive

Additive 2

Additive 9

Additive 4 (strong foaming)

Additive 8



Additive 1

Additive 6

Additive 11 (hard sedimentation)

Additive 10

Additive 5

Additive 7

Sample	Additive Loading	PS Matt 112 maximum usage	Others
No additive		16%	
Additive 1	3.0%	16%	
Additive 2	3.0%	16%	
Additive 3	3.0%	15%	
Additive 4	3.0%	16%	strong foaming
Additive 5	3.0%	16%	
Additive 6	3.0%	16%	
Additive 7	3.0%	16%	
Additive 8	3.0%	16%	
Additive 9	1.5% 1.5%	16%	
Additive 10	1.5%	26%	
Additive 11	1.5%	30%	hard sedimentation




# PS Matt 601 (Solventbased butyl acetate)

ELEMENTIS

#### **RESULTS**

% = concentration PS Matt 601



Sample	Additive Loading	PS Matt 601 maximum usage
No additive		14%
Additive 13	2.5%	16%
Additive 14	5.0%	28%
Additive 15	7.5%	34%
Additive 16	5.0%	18%
Additive 17	7.5%	22%
Additive 18	5.0%	18%
Additive 19	7.5%	18%